



中国认可
国际互认
检测
TESTING
CNAS L11969



Stacking Test Report

堆码试验报告

Client 委托方	Shenzhen Jinpinneng Electronics Co., Ltd. 深圳市劲品能电子有限公司
Add. of Client 委托方地址	No.138, Pengda Road, Nanlian Community, Longgang Street, Longgang District, Shenzhen 深圳市龙岗区龙岗街道南联社区鹏达路 138 号
Name of Goods 货物名称	Li-ion Battery 18650-1200mAh 3.7V 4.44Wh 锂离子电池 18650-1200mAh 3.7V 4.44Wh
Testing Laboratory 检测机构	NRCC (Shenzhen) Safety Technology Co., Ltd. 诺诚 (深圳) 安全科技有限公司 (Testing and Inspection Body affiliated to the National Registration Center for Chemicals, MEM) (应急管理部化学品登记中心旗下检测检验机构) Building A, No. 2, Tengfeng 5th Road, Fuyong, Bao'an District, Shenzhen 深圳市宝安区福永街道腾丰五路 2 号 A 栋 Phone number 电话号码: +86-755-27322216 Email 邮箱: service@nrccsafety.com Website 网址: www.nrccsafety.com
Report No. 报告编号	241220070422-48
Issued Date 签发日期	2024.12.16
Test Conclusion 检测结论: Shown in the conclusion of test report. 见检测报告结论页。	

Tested by主检人:

(Engineer 工程师)

Lidao Cai 吕道才

Approved by审批人:

(Manager 经理)



Duan Pike 段 子明



堆码试验报告



Name of Goods 货物名称	Li-ion Battery 18650-1200mAh 3.7V 4.44Wh 锂离子电池 18650-1200mAh 3.7V 4.44Wh		
Manufacturer of package 包装件生产企业	Shenzhen Jinpinneng Electronics Co., Ltd. 深圳市劲品能电子有限公司		
Manufacturer of packaging container 包装容器生产企业	Zhongshan Tengfeng Paper Packaging Products Co., LTD 中山市腾丰纸类包装制品有限公司		
Detailed description of the package 包装件详细说明	Corrugated carton, Size: 440*235*190mm, Carton thickness: 6mm, Packaging auxiliaries: Paper box 瓦楞纸箱, 尺寸: 440*235*190mm, 纸箱厚度: 6mm, 衬垫材料: 纸盒		
Detailed description of the contents 内装物详细说明	Li-ion Battery, Model: 18650-1200mAh, Basic parameters: 3.7V, 1200mAh, 4.44Wh, Quantity: 162PCS 锂离子电池, 型号: 18650-1200mAh, 基本参数: 3.7V, 1200mAh, 4.44Wh, 数量: 162PCS		
Number of samples 样品数量	3 packages /3 个包装件		
Gross weight per package 每包装件毛重	7.6kg		
Total load 加载的载荷	114kg	Ambient Conditions of sample preparation 样品预处理环境	环境温度: 23°C±2°C 相对湿度: 50%±2%
Test Standard 检测标准	"Recommendations on the Transport of Dangerous Goods, Model Regulations" Twenty-third revised edition (ST/SG/AC.10/1/Rev.23 (Vol.II) 6.1.5.6). 《关于危险货物运输的建议书 规章范本》第二十三修订版 (ST/SG/AC.10/1/Rev.23 (Vol.II) 6.1.5.6)。		
Test Item 检测项目	3m Stacking Test 3m 堆码试验		
Test Result 检测结果	After the 24h stacking test, batteries are not damaged, packages are not damaged, no leakage, no deformation. 包装件在经受 24h 堆码试验后, 电池未见受损、包装未见破损、未见泄漏、未见变形。		
Test Conclusion 检测结论	After testing, the package has passed the stacking test of "Recommendations on the Transport of Dangerous Goods, Model Regulations" Twenty-third revised edition (ST/SG/AC.10/1/Rev.23 (Vol.II) 6.1.5.6). 经检测, 该包装件通过了《关于危险货物运输的建议书 规章范本》第 23 版 (Vol.II) 6.1.5.6 的堆码试验。		
Test Start Date 测试开始日期	2024.12.03	Test Completion Date 测试完成日期	2024.12.09

Photos 照片

Package 包装件:



Inner content 内装物:



注意事项 Important Notice

1. This report is invalid until signed by the approver and sealed by the NRCC (Shenzhen) Safety Technology Co., Ltd. (Hereinafter referred to as "the Laboratory").

本报告无审批人签字和诺诚（深圳）安全科技有限公司（以下简称“实验室”）签章无效。

2. This report is invalid with any unauthorized altered, forgery, falsification, or partial replication.

本报告经伪造、篡改、删除、部分复制均无效。

3. This report is only valid to the test conclusion under the precondition that the client submitted real entrusted materials and samples, and the test conclusion result is not relevant to other materials sharing the same name or congeners.

本报告的检测结论仅在委托方提交的委托资料和样品真实的情况下有效，检测结论与样品名称及其他同类物质的检测结论无关。

4. When significant changes in the manufacturing process, materials, components, or other factors of the package may change its hazard classification, this battery should be identified again; If relative regulations or standards update, the conclusions may change, and the batteries should be identified again.

如包装件的生产工艺、原材料、组分等因素有较大改变，可能使其危险性发生改变时，应重新进行检测；当检测报告所依据的法规、标准发生变化时，其检测结论可能发生变化，应重新进行检测。

5. Objections to the test report must be submitted to the Laboratory within 15 days.

对报告书若有异议，应于收到报告之日起 15 天内向实验室提出。

6. Should there be any inconsistencies between Chinese and English content in this report, the Chinese version shall prevail.

本报告中英文内容出现不一致时，以中文内容为准。

7. Visiting www.nrccsafety.com, or contact us by telephone, email could check report authenticity.

可访问 www.nrccsafety.com，或通过电话、电邮查询报告真伪。

*****End of Report 报告结束*****